

Terracotta Earthenware/Stoneware Clay

Name	Brief Description	Temperature	Price per bag (12.5kg unless otherwise stated)
1137 Standard Smooth	Throwing and hand building	1040 - 1160°C	£5.26
VR Smooth	Good throwing and casting properties. Smooth Texture. Red/Brown.	1080 - 1150°C	£5.34
GVR10 10% Sanded	10% addition of 40's - 90's sand, improves strength in throwing and increases resistance to cracking and warping	1080 - 1180°C	£5.88
GVR20 20% Sanded	20% addition of 40's - 90's sand, improves strength in throwing and increases resistance to cracking and warping	1080 - 1180°C	£5.00
GVRs	Good degree of medium to coarse grog. Gives open texture yet retaining a good degree of plasticity. Has good resistance to thermal shock.	1080 - 1220°C	£6.03
1132 New Keuper Red	New formulation of previous Keuper Red.	1080 - 1250°C	£10.51
E/S 75 Smooth Textured Crank	A fine grogged alternative to ES 65. It will take surface detail well, can be used as a coarse throwing body and is excellent for slabbing, handbuilding and tiles.	1080 - 1220°C	£8.96
E/S 65 Crank	Enabling you to create large sculptural pieces without the risk of lime popping, commonly associated with grogged reds	1080 - 1220°C	£8.97
1188 Air hardening (Red)	Standard potters modelling clay with an addition of nylon fibres to provide exceptional bonded strength when dry and unfired.	1000 - 1050°C (or can be left unfired)	£9.43
Paperclay E/S800	Smooth/medium body.	1060 - 1160°C	£10.29 (5kg bag)